

TECHNICAL DATA SHEET

PRODUCT: BC307 BLACK HI-OP 1K ETCH COATING

DESCRIPTION: BC307 Black Hi-Op 1K Etch Coating is a high performance polyvinyl butyral and epoxy based, self-etch coating formulated to provide adhesion and anti-corrosive properties on ferrous metals, zinc coated steels (including galvanized iron) and non-ferrous metals such as aluminium.
It has a smooth, matte surface with good covering power and functions by adhering to the base surface and providing good adhesion for subsequent finishing coats such as 2-pack polyurethanes, enamels and lacquers.

COLOURS: Available in Black.

FEATURES: Use as a self-etching topcoat for interior use.
Fast through dry.
Can be recoated at anytime after the film has dried.
Can be left uncoated for up to 3 months for exterior use without film degradation.
Corrosion resistant.
Zinc chromate free.
Spray application.

AREAS OF USE: For general industrial use on metal fabrications, implements, structural steel for buildings, purlins, gates, cranes, trusses, agricultural parts.
For exterior use should be over-coated with appropriate finish coat as soon as Practically possible.
For interior use apply a second coat of BC307 Black Hi-Op 1K Etch Coating as the finishing coat.

APPLICATION GUIDE: Stir thoroughly too uniform consistency before using.
BC307 Black Hi-Op 1K Etch Coating is supplied ready for use straight from the can, but can be reduced up to 15% by volume with BC307 Etch Thinner for use with conventional spray systems.
Apply 2 - 3 cross passes to obtain a smooth, even finish which covers the entire surface.
Allow adequate flash off time between passes and/or coats and do NOT attempt to speed up the drying process by blowing compressed air onto the job.
Failure to follow these instructions can cause ridging, splitting and/or cracking of the surface.
Allow to dry for 30 - 60 minutes before recoating with enamels and allow to dry approximately 2 hours before recoating with lacquers or urethane finishes.

TECHNICAL DATA SHEET BC307 BLACK HI-OP 1K ETCH COATING

APPLICATION GUIDE: (continued)

Do **NOT** apply to lead.
Not suitable for prolonged exterior exposure as a one coat finish.

BC307 Black Hi-Op 1K Etch Coating contains flammable solvents.

Keep away from heat and open flame.

When applying in a confined space use an air line respirator.

Should not be allowed to remain on the skin and normal hygiene standards should be observed when using this product.

SURFACE PREPARATION :

Repair any surface defects prior to painting.

All surfaces to be painted must be sound, suitably cleaned, degreased and dried.

<u>SURFACE</u>	<u>PREPARATION</u>	<u>SYSTEM</u>	<u>DRY FILM THICKNESS</u>
Structural steel	Abrasive blast clean to AS1627.4 Class 2	First Coat : BC307 Black Hi-Op 1-K Etch Coating Second Coat : BC307 Black Hi-Op 1-K Etch Coating or UT100 U-thane or BC100 Fast Dry Enamel	15 microns 15 microns 50 - 100 microns 40 microns
Mild steel, galvanized / zinc coated steel, aluminium	Remove any rust, corrosion products, grease, oil, dirt, moisture. Degrease thoroughly. Let dry completely	First Coat : BC307 Black Hi-Op 1-K Etch Coating Second Coat : BC307 Black Hi-Op 1-K Etch Coating or UT100 U-thane or BC100 Fast Dry Enamel	15 microns 15 microns 50 - 100 microns 40 microns

AIR DRY SCHEDULE:

Dust Free Time	5 minutes
Touch Dry Time	5 - 10 minutes
Print Free Time	30 minutes
Hard Dry Time	4 hours
Force Dry Time	10 Minutes at 90 - 120 °C
Dry To Recoat Time	
ENAMELS	30 - 60 minutes
LACQUERS / URETHANES	2 hours

NOTE: *Drying times are dependent on film build and ambient weather conditions.*



Manufacturers of UTHANE Polyurethane Coatings
14a Williamson Road, Ingleburn, NSW, 2565
Phone +612 9729-2000 1300 BCC OAT (222 628)
Email: orders@bccoatings.com.au
Text Orders/Enquiries: 0487 800 090

TECHNICAL DATA SHEET **BC307 BLACK HI-OP 1K ETCH COATING**

TYPICAL PROPERTIES:

- Gloss** : Satin
Shelf Life : 6 - 12 months in original sealed containers
Flash Point : < 10 °C, Classification 3.1
Durability : Exterior - very good with suitable topcoats.
Interior - very good without topcoats.

RESISTANCE PROPERTIES

- Abrasion** : Fair
Heat : Up to 120°C dry heat
Solvent : Good for hydrocarbons.
Not recommended for exposure to alcohols, esters or ketones
Water : Good
Chemical : Fair
Immersion : Not recommended.

This data sheet is based on information in BC Coatings possession at date of issue.
BC Coatings supplies its products only on condition that the consumer is satisfied as to the performance of the product in meeting their particular requirements.