

## TECHNICAL DATA SHEET

**PRODUCT:** UT400 CLEAR POLYURETHANE SEALER

**DESCRIPTION:** UT400 2-Pack Clear Sealer is an acrylic Polyurethane designed to give a natural finish to timber, veneers etc.

The product has been designed as a first coat for the UT400 Series Topcoats (UT405, UT410, UT430), to provide the maximum Ultra-Violet protection and to prevent discolouration to cabinets etc, exposed to intermittent sunlight.

Its principal area of application of the system is in the decoration and protection of man-made veneers such as "New Age" veneers and is used in the cabinet and wall panel industries.

### PROPERTIES

**COLOUR** : Milky, dries clear

**UV RESISTANT** : Excellent

**CHEMICAL RESISTANCE** : Very good

**SOLVENT RESISTANCE** : Very good.

**ABRASION RESISTANCE** : Very good.

**SANDABILITY** : Very good.

### TECHNICAL DATA

**RECOMMENDED FILM BUILD** : 100 microns (wet) 25 microns (dry)

**VOLUME SOLIDS** : 25 %

**THEORETICAL COVERAGE** :  $\approx 10 \text{ metres}^2$  per litre at 100 microns wet.

This will vary depending on the porosity of the substrate

**COMPONENTS** : Two.

**MIXING RATIO** : 10 parts Part "A" : 1 part Part "B" (UT4400) by volume

**DRYING @ 25°C** : Touch dry: 20 mins Handleable: 2 hrs  
Recoat: 2 hrs Full cure: 5 days

**PART B** : UT4400 Hardener

### UT400 CLEAR POLYURETHANE SEALER

<b>POT LIFE @ 25°C</b>	:	6hrs.
<b>APPLICATION METHODS</b>	:	Air or airless spray. Air.
<b>FLASHPOINT</b>	:	23° C
<b>SHELF LIFE</b>	:	12 months (min)
<b>PACKAGING</b>	:	Part A            4 lt,     20 lt. Part B            0.4lt,    2 lt.

---

#### SURFACE PREPARATION:

- Lightly sand board to remove scratches.
- Lightly sand edge strip to reduce edge veneer finger glue line.

#### **MIXING:**

Stir each of the components till homogenous.  
Mix all base and hardener components until fully blended.  
Allow induction time of 10 - 15 minutes prior to commencing application.  
For smaller quantities mix 10 parts of base to 1 part hardener by volume.

#### **THINNING:**

Use UT100 Thinner only, thin 20% by volume.

#### **EQUIPMENT CLEANUP:**

All equipment should be thoroughly cleaned with UT100 Fast Thinner.

## UT400 CLEAR POLYURETHANE SEALER

### APPLICATION:

- Gun pressure for all coats to be set at 310 kPa (45 psi) on regulator with the gun control valve fully open.
- Apply 1<sup>st</sup> seal coat of UT400 CLEAR SEALER (thinned with 20% UT100 Fast Thinner)
- Whilst still wet, apply 2<sup>nd</sup> seal coat of UT400 CLEAR SEALER (thinned with 20% UT100 Fast Thinner)
- Application rate for seal coats is 100mls. per square metre of board.
- Allow to dry.
- Lightly sand board.
- Clean board with solvent to remove sanding dust prior to application of top coat.
- Apply 1<sup>st</sup> top coat of UT405, UT410 or UT430 (thinned with 20% UT100 Fast Thinner)
- Whilst still wet, apply 2<sup>nd</sup> top coat (thinned with 20% UT100 Fast Thinner)
- Application rate for top coats is 100mls, per square metre of board.
- Allow 24 hours drying time prior to transport.

This data sheet is based on information in BC Coatings possession at date of issue.

BC Coatings supplies its products only on condition that the consumer is satisfied as to the performance of the product in meeting his particular requirements.