

> Email: <u>orders@bccoatings.com.au</u> Text Orders/Enquiries: 0487 800 090

#### TECHNICAL DATA SHEET

PRODUCT UW1101 WATERBORNE TOPCOAT

**DESCRIPTION** UW1101 is a single component, very low VOC levels, non-yellowing, water

borne coating designed as a quality finish coat compatible with both 1K and 2K

Undercoats.

**PROPERTIES** 

**COLOUR** White and a range of colours

GLOSS LEVEL Satin (25-30%)

**CHEMICAL** 

**RESISTANCE** Good.

**SOLVENT** 

**RESISTANCE** Good

**ABRASION** 

**RESISTANCE** Good

VOC LEVEL <30g / Litre

TECHNICAL DATA
RECOMMENDED FILM

**BUILD** 40 microns (wet)

VOLUME SOLIDS 25 %

**THEORETICAL** 

**COVERAGE** 12 sq metres / lt. (approx).

**DRYING AT 25** °C Touch Dry 30 -40minutes

Handleable 40 - 60minutes

Sanding 2 hours

<u>Note</u> - dry times are listed for normal ambient conditions, however the drying rate is dependent on the Temperature and Relative Humidity – low temperatures and/or high Relative Humidity will retard the drying of water borne coatings



Email: orders@bccoatings.com.au

Text Orders/Enquiries: 0487 800 090

#### TECHNICAL DATA SHEET

### **UW1101 WATERBORNE TOPCOAT**

APPLICATION

**METHODS** Conventional, airless or air assisted airless.

**FLASHPOINT** Non flammable

**RECOATABILITY** Must be sanded.

**SHELF LIFE** 12 months at 25 °C in original sealed containers.

**PACKAGING** 4 litre & 10 litre

#### SYSTEM RECOMMENDATIONS

<b>SUBSTRATE</b>	<b>PREPARATION</b>	COATING	FILM BUILD
		<u>SEQUENCE</u>	WET (DRY)
TIMBER, MDF,	Sand and	1 <sup>st</sup> coat:	
MELAMINE	remove dust	Suitable IK or 2K Polyurethane Undercoat	60 - 80 microns
TREATED MDF		W/B or Solvent Based	
	Sand and remove	2 <sup>nd</sup> coat:	
	dust	UW1101 Pigmented Finish	80 - 100 (26 - 34) microns

**NOTE** UW1101 Waterborne Topcoat can be applied over both UT240 Polyurethane

Undercoat, and PE230 Polyester Undercoat / Sealer, however they **must** be

allowed to cure thoroughly overnight before being overcoated

UW1101 can be applied directly to sanded Melamine Treated MDF

Date Of Issue: 17/05/2020 Page 2 of 4 TDS00266 V2



> Email: <u>orders@bccoatings.com.au</u> Text Orders/Enquiries: 0487 800 090

## TECHNICAL DATA SHEET

# <u>UW1101 WATERBORNE TOPCOAT</u>

**APPLICATION** 

MIXING Stir the UW1101 thoroughly before use with a flat blade stirrer. Mechanical

stirring is recommended to ensure uniform colour and opacity

**THINNING** UW1101 can be thinned up to 15% with water

**SPRAYING** Conventional Spray Gun with a 2mm tip at a pressure of 350 – 600Kpa

**EQUIPMENT CLEANUP** 

All equipment should be thoroughly cleaned using water.

<u>Note</u> Do not use Spray guns for this product that have been used to apply solvent based products, and hence do not use the spray equipment that has applied the water borne products with Solvent based products.

#### **PRECAUTIONS**

**SAFETY** Provide adequate ventilation during use.

Airflow should be adequate to ensure a comfortable working atmosphere. When spray painting, users should comply with the provisions of the State

Spray Painting Regulations.

Avoid contact with skin and eyes.

Wear protective goggles and gloves when handling the material.

In the case of skin contact, remove contaminated clothing and wash skin

thoroughly with clean water.

Seek medical attention if eyes are affected by splashes or fumes.



> Email: <u>orders@bccoatings.com.au</u> Text Orders/Enquiries: 0487 800 090

## TECHNICAL DATA SHEET

## **UW1101 WATERBORNE TOPCOAT**

**GENERAL** 

Rate of cure is dependent upon temperature.

Do not apply this product at temperatures below 10  $^{\circ}$ C or relative humidifies above 85 %.

Shelf life is normally 12 months but depends on storage conditions.

This data sheet is based on information in BC Coatings possession at date of issue.

BC Coatings supplies its products only on condition that the consumer is satisfied as to the performance of the product in meeting his particular requirements.

Date Of Issue: 17/05/2020 Page **4** of **4** TDS00266 V2