

Technical Data Sheet

FORTIS CONCRETE SHEILD™ ACRYLA PAVE

FEATURES

- Fast drying
- Easy to apply
- Non-yellowing
- Clear gloss finish
- Wet-look
- Resistant to oil, grease, & dirt
- Excellent durability
- Trafficable
- Low Odour
- Eco friendly
- VOC free

TYPICAL APPLICATION

Suitable for untreated concrete driveways and pavement, including coloured concrete, exposed aggregate, and pattern pave

TECHNICAL DATA

Colour: Opaque liquid (Dries Clear)
Application temperature: 10 to 35°C
Coverage: 12-15 m²/ L for porous surfaces, 35-40 m²/ L smooth dense surfaces
pH: 8.0-9.5
Pack size: 5L, 15L
Shelf Life: 12months @ 25°C unopened



Fortis Adhesives & Coatings
14 Commercial Drive
Dandenong South,
Victoria, Australia, 3175
www.fortisadhesives.com.au
+61 3 97065448

FORTIS CONCRETE SHEILD™ ACRYLA PAVE is a premium grade fast drying water based acrylic sealer specifically designed for driveways and paving. It provides a protective gloss 'wet-look' layer which provides resistance to oil, grease, dust and dirt.

SURFACE PREPARATION

When using Acryla Pave for the first time, or on a new floor always test a small inconspicuous area with a 24-hour cure time to determine ease of application and desired results. Make sure surface is clean, free of waxes, coatings, and previous sealers, and is dry for 24 hours. Clean surface with minimum 2000psi pressure washing. Heavily solid/dirty surfaces will require a light acid clean such as 20:1 mix of HCl diluted in water. Mix 20parts water with 1part HCl. Rinse well after cleaning and allow 24hrs drying time before application of the Acryla Pave. Surface temperature should be between 10°C and 35°C. Ensure that the area is well-ventilated during cleaning & application and until the surface is dry.

APPLICATION

Apply a thin uniform layer of Acryla Pave with a lamb's wool applicator or roller brush. Allow 2 hours drying time (25°C & 65% humidity) or wait until the entire area is touch dry before application of additional coats. Apply subsequent coats in the same manner and if preferred machine buff after applying the 3rd or 4th coats ensuring the surface has had at least 4 hours to dry. A minimum of 2 coats are recommended. Ensure sealer is not applied too thick and is applied evenly. Do not allow any pooling to occur. Full cure is achieved after 24-72 hours. Avoid any foot traffic for 6-8 hours after application.

PLEASE NOTE: This product can cause decreased slip resistance for wet areas such as paving surrounding pool areas etc. It is subsequently not recommended for areas frequent to water exposure.

MAINTAINANCE

A recoating is recommended every 2 years and may be necessary more frequently in very high traffic areas. For previously polished floors make sure you create clean and smooth surface prior to application. Remove any uneven surfaces of polish accumulation as well as any deep scratches or ingrained soil. When applying Acryla Pave to already sealed concrete if the previous coat is not Acryla Polish or Acryla Seal the floor should be tested to confirm if the existing sealer is suitable to be resealed over.

PLEASE NOTE: If the previous coat was Acryla Seal but it was applied over 3 years prior cross-hatch test is recommended.

THE CROSS-HATCH TEST

Select a high traffic area of the floor and Apply the sealer, as per the application instructions below, to a 1m² area. Use a sharp blade to cut a light "cross-hatch" pattern through the sealer. Place a piece of clear self adhesive packing tape over the cross-hatch area. Press firmly for maximum adhesion and remove sharply. Repeat with fresh tape several times. If sealer is present on the tape, the sealer should be completely stripped from the surface prior to coating the floor. If there is no sign of sealer adhering to the tape or delaminating from the surface, the bond of the existing sealer is sufficient for resealing.

PLEASE NOTE: if current sealer shows signs of whitening or blooming, regardless of cross hatch test results, sealer may need to be stripped completely from the surface. Whitening may reoccur if new coat of sealer is applied over this problem.

SAFETY

Please refer to Material Safety Data Sheet prior to use.

For further information, refer to the Fortis website www.fortisadhesives.com.au

Disclaimer

Fortis products should be used in accordance with the information contained here. Each user should read and consider this information carefully in the context of how the products will be handled and used in the workplace including in conjunction with other products. While the information contained here is to the best of our knowledge at the date of publication, Fortis makes no representation about the accuracy of the information. If you need clarification or more information, you should contact Fortis Adhesives & Coatings office directly. Fortis products are sold without express or implied warranties, other than as provided by statute, and subject to our standard terms and conditions (provided to customers and available on request). Subject to our standard terms and conditions, and any statutory provisions, Fortis accepts no responsibility (including in negligence) for loss or damage of any nature resulting from the use of Fortis Adhesives & Coatings products or reliance upon the information contained here