

ULTIMATE

Two-Pack Epoxy Gloss

Product Code: U2EG

Product Description

Haymes Ultimate Two-Pack Epoxy Gloss is a unique, environmentally responsible water-based epoxy coating system. Ultimate Epoxy Gloss has superb film properties, adhesion, and surface hardness. Offering excellent chemical, water and surface resistance with an easy-to-clean finish, it is an ideal floor coating. Various non-slip ratings are readily achievable through the addition of suitable media.



Key features:

- ✓ Self-priming
- ✓ Low odour / VOC
- √ Superior food-grade coating
- ✓ Excellent chemical resistance
- ✓ Easy to clean

Typical Applications

Concrete floors, concrete walls, masonry, slate, and steel in applications such as;

- Flooring and seamless flooring
- Factories, warehouses, garages and workshops
- Hospitals and shopping centres
- Primed steel as a build or barrier coat

- Food & beverage industry / Cool rooms
- Schools and laboratories
- Retaining walls

Typical Properties			
Vehicle type	Ероху		
Hardener	Polyamide		
Mixing ratio	2: 1 by volume (Pack A: Pack B). These products MUST BE POWER STIRRED. Power stir Parts A and Part B separately, then together as A+B on high speed		
	ensuring components blend thoroughly.		
Pot life	Approximately 1 hour @ 25 °C		
Finish	Gloss		
Colour	White. Tintable		
Sizes	3 L, 15 L		
Clean-up	Water		
Coverage	Up to 6 m ² /L		
Dry time	Touch dry: 3 - 5 hours based on adequate airflow		
·	Recoat: 4 - 6 hours based on adequate airflow		
Film build	Wet: 170 um		
	Dry: 75 um		
Application tools	Airless spray (15 – 21 thou tip) at 1700 - 2100 psi		
	Synthetic brush or epoxy roller sleeve		

Technical Data	
Volume solids	47%
VOC	89-118 g/L depending on colour. Confirm
Abrasion resistance	Excellent. Note: Good mar resistance can be achieved for dark or strong colours with a final coat of Ultimate Two-Pack Epoxy Clear Gloss.
Chemical resistance	Alkali – Excellent; Acid – Fair to very good.
Dry heat resistance	120 °C
Solvent resistance	Excellent
Salt spray resistance	Very good
Durability	Excellent. Interior use only. Polyurethane topcoats are required for UV resistance.

Dry Times				
Temperature	Touch dry	Hard dry (hours)	Full cure	
25 °C	3 – 5 Hours	18 - 24 Hours	7 Days	
15 °C	5 - 8 Hours	32 - 40 Hours	10 Days	
10 °C	8 -11 Hours	48 - 60 Hours	15 Days	

NOTE: The application of water-based epoxy at low temperatures can cause amine bloom. This shows as low gloss and a cloudy effect on the coating surface. High humidity will also slow down the cure and may cause amine bloom. Water-based coatings should be applied when the humidity is below 80%. At cooler temperatures or higher humidity, drying times will be extended. **You must ensure adequate airflow over coated surfaces to ensure the coating dries and hardens.** As the size, location and weather conditions of projects vary, you must consult with a Haymes Paint representative on the need for industrial exhaust fans and ventilators to provide adequate airflow for your project.

Surface Preparation	
General surface preparation	All surfaces must be structurally sound, clean, dry and free of
	contamination, particularly salt deposits.
	Loose or flaking paint must be removed by abrasive blast cleaning, power
	tool cleaning or sanding, to AS1627.
Previously painted surfaces	 Previous coatings should be abraded prior to painting
	All surfaces should be free from oil, grease, loose paint, and other
	contaminants.
	3. Oil, grease, dirt, and other contaminants must be removed with detergent
	and water blasting or solvent cleaning to AS1627.1.
	4. A test patch is always recommended before use. Adhesion of the test
	patch should be checked prior to painting the entire surface.
Concrete	Allow new concrete surfaces to cure for a minimum of 28 days before
	painting.
	2. Surface to be painted should be free from oil, grease, and other
	contaminants.
	3. Moisture content should be less than 5.5%.
	4. Grind the surface to remove laitance and provide key. To get a uniform
	surface profile, use shot blasting, diamond grinding or acid etch.
	5. Prime the surface with Ultimate Satin Epoxy to achieve maximum
	adhesion and durability.
Steel structures	Degrease the surface and remove all weld spatter and flux.
Ctool of dotal oo	Grind sharp edges and corners.
	3. For best results, abrasive blast clean to AS1627.1 to 9.
	4. Apply a suitable primer according to specification. In corrosive
	environments steel typically requires an anti-corrosive primer as a barrier
	coat.

Aluminium, galvanised iron & Zincalume®	1. 2.	Remove oil and excess grease with a mild detergent or with sugar soap. Slightly roughen the surface with the help of sanding or light whip-blasting
	3.	with a non-metallic abrasive. Apply a suitable primer according to specification.

Precautions

- Do NOT apply if the ambient temperature is less than 10 °C or greater than 35 °C or if conditions will drop below 10 °C during the drying period.
- Not to be applied above 80% relative humidity.
- Chalking will occur during full sunlight exposure without loss of film integrity. Can be over coated with Haymes Ultimate Polyurethane for UV resistance.
- Always ensure adequate airflow and ventilation during both application and drying period.
- Please check the colour for accuracy prior to application. Haymes paint accepts no responsibility for the application of incorrect colours.
- Not suitable for tiles.
- Due to the chemical composition of tyres, contact between tyres and this coating may result in tyre staining. Given the wide variation in tyre composition and age, Haymes Paint makes no warranties as to the performance of the coating and potential tyre staining.

Application

- **Mixing**: Parts A and B must be power stirred separately then together thoroughly for at least two minutes before thinning, without causing an excess of foam.
- Once units of paint have been mixed they should not be resealed. After prolonged breaks, it is recommended that work recommences with freshly mixed units.
- Stir thoroughly before and during application.
- Apply two coats by brush, roller, or spray to achieve sufficient film build.
- Abrade if recoating after 7 days.

Thinning

Maybe thinned with up to 10% clean water to achieve acceptable atomisation. Thinning may necessitate the application of additional coats to achieve sufficient film build.

Clean-up

Do not allow material to remain in hoses, gun, or spray equipment. Thoroughly flush all equipment with water. Clean all equipment after use with water, detergent solution, or methylated spirits. It is good work practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time.

Safety and First Aid

WARNING – Hazardous material. Keep out of reach of children. Read label before use. Avoid breathing fumes, mists, vapours, or spray. Do not get in eyes, on skin, or on clothing. Wear protective gloves, protective clothing and eye or face protection. Wash contacted areas thoroughly after handling. Contaminated work clothing should not be allowed out of the workplace. Take off contaminated clothing and wash before reuse. IF SWALLOWED: Rinse mouth. Do NOT induce vomiting. Causes skin irritation. May cause an allergic skin reaction. IF ON SKIN: Wash with plenty of soap and water. If skin irritation or rash occurs, get medical advice. Additional information is listed in the safety data sheet. Causes eye irritation. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists, get medical advice.

For further safety information please refer to the product Safety Data Sheet available at <a href="https://www.haymespaint.com.au/products/technical/product-data-sheets-and-safety-dat

Storage

Store in a dry place. Store in a closed container. Protect from sunlight. Store between 5 °C and 30 °C.

Protect Our Environment

Even though the Ultimate range of low VOC and low odour products are water-based, NEVER allow any leftover product to enter drains or waterways. Dispose of hardened product in general waste or, for large quantities, via chemical waste disposal. For non-mixed components, retain in a marked, sealed container for future use or dispose of via special chemical waste collection programs. Dried empty containers can be recycled and should be disposed of via recycling facilities. If they cannot be recycled, dispose of contents to an approved waste disposal plant and containers to landfill.

Manufacturer's Comment

This product has been designed as part of a totally integrated application system. Use with any other manufacturer's product(s) or failing to follow application instructions may result in detrimental effects on product performance for which Henry Haymes Pty. Ltd. cannot be held responsible. Further information is available in the form of safety data and product information sheets from Haymes Paint (1800 033 431). We continually update materials and methods; please ensure you have the latest information.

Disclaimer

Due to the chemical composition of tyres, contact between tyres and this coating may result in tyre staining. It is important to understand the limitations of this coating product for resistance to tyre staining also known as "paw printing". Given the wide variation in tyre composition and age, Haymes Paint makes no warranties as to the performance of the coating and potential tyre staining and will not be held liable for any claims made where tyre staining occurs. You must read the specific product data sheet and fact sheet on tyre staining before commencing application of this product. These documents provide information about the suitability and application of the product for specific purposes. If you require more information or a product with resistance to tyre staining, then you must contact Haymes Service Express who can refer a technical representative for specific recommendations for your project before commencing any work.

The information provided is correct at the time of preparation; however, it is the responsibility of those using this information to check that it is current prior to specifying, recommending, or using product contained in this information. Because use conditions and applicable laws may differ from one location to another and may change with time; those using this information are responsible for determining whether products and the information in this document are appropriate for their use and for ensuring that workplace and disposal practices are in compliance with applicable laws and other government enactments. Haymes Paint assumes no obligation or liability for the information in this document. No express warranties are given except for any applicable written warranties specifically provided by Haymes Paint. All implied warranties including those of merchantability and fitness for a particular purpose are expressly excluded.

Henry Haymes Pty Ltd A.B.N. 14 004 201 638 Waringa Drive Wendouree Industrial Estate Ballarat Vic 3350 Freecall 1800 033 431 Freefax 1800 801 892 www.haymespaint.com.au

Date of Preparation 14/9/2020 Versioned