

# **HAYMES PAINT INDUSTRIAL COATING SOLUTIONS**

# 304 2K Satin Acrylic Polyurethane

Product Code: I304SB

# **Product description**

Haymes Paint Industrial Coating Solutions 304 2K Satin Polyurethane is a 2K acrylic urethane topcoat, characterised by its durability, excellent flow and gloss. It is suitable for most industrial and commercial applications.



# **Key Features**

- √ Superior performance
- ✓ Satin finish
- ✓ Quick and easy application

# Where to Use (Substrates)

Mild steel, aluminium, galvanised iron, glass reinforced plastics (GRP) and previously painted substrates in sound condition.

Product Name	Volume Solids %	Weight Solids %	Density g/mL	VOC g/L
304 2K Satin Acrylic Polyurethane	43.3	49.4	1.019	516.0
PU Hardener (4:1) Normal	33.9	39.9	0.986	593.1
PU (4:1) Fast	33.6	40.2	0.968	578.3
PU (4:1) Slow	35.4	40.9	1.004	593.8

Surface Preparation	
Mild Steel	DTM: Sand with 240 Frecut <u>Primer</u> : Apply Haymes Paint Industrial Metal Etch Primer or Haymes Paint Industrial Universal Primer. Sand with P600 wet or dry.
Aluminium	Primer: Apply Haymes Paint Industrial Metal Etch Primer or Haymes Paint Industrial Universal Primer. Sand with P600 wet or dry.
Galvanised Iron	Primer: Apply Haymes Paint Industrial Metal Etch Primer or Haymes Paint Industrial Universal Primer. Sand with P600 wet or dry.
Glass Reinforced Plastics (GRP)	Primer: Apply Haymes Paint Industrial Metal Etch Primer or Haymes Paint Industrial Universal Primer. Sand with P600 wet or dry.
Previously painted Surfaces (in sound condition)	Sand with P600 wet or dry.

# **Special Notes:**

- All surfaces must be thoroughly sanded and cleaned with Haymes Wax & Grease Remover prior to application.
- Surfaces must be clean, bare, dry and free of dust, wax, grease, surface contamination and oxidation prior to painting.
- Use white or light-coloured primers under bright yellows, oranges and reds, if required.
- The above systems are examples only. For further information, please contact Haymes Paint on 1800 033 431.

Product Preparation				
	<ul> <li>Weigh the concentrates into the required base in accordance with the relevant colour formula.</li> <li>A maximum of only 10% reduced concentrates is allowed and a maximum of 35% for all concentrates, in total.</li> <li>Stir or shake for a minimum of 10 minutes.</li> <li>Never leave the mixture stand for more than 30 minutes before mixing.</li> </ul>			
Mixing Ratio 4:1 (by volume)	Haymes Paint Industrial Coating Solutions 304 2K Satin Acrylic Polyurethane		Haymes Paint Industrial Coating Solutions 4:1 Polyurethane Hardener	
	4	parts	1 part	
Reducer	Up to 20% (v/v) Hayn	Up to 20% (v/v) Haymes Paint Industrial Coating Solutions Universal 2K Thinner, if required.		
Matting (if required)	Matt Finish: Add 20% of 399 Flattening Base. Notes:  • 399 Flattening Base must be added before adding a hardener or thinner. • The addition of 399 Flattening Base will reduce coverage.			
Pot Life @ 25C	2 - 3 hours			
S	BSB 4 Cup	18 to 20s		
Spray viscosity @ 25C	Ford 4 Cup	16 to 17s		
Spray Equipment	Gun type	Fluid tip	Spray pressure	Spray distance
	Gravity Feed	1.2 to 1.4mm	2.0 – 2.4bar 30 - 35psi	15 - 20cm 6 - 8inch
	Suction Feed	1.5 to 2.0mm	2.0 – 2.4bar 30 - 35psi	15 - 20cm 6 - 8inch
HVLP	HVLP	1.2 to 1.3mm	0.4 - 0.7bar 6 - 10psi	15 - 20cm 6 - 8inch

Product Preparation		
	Airless, Air Assisted, Electrostatic	Consult the spray gun manufacturer's instructions.

Product Preparation (continued)				
	Number Of coats	2 - 3	Apply one light coat followed by one or two even full coats. Avoid heavy wet coats.	
	DFT Recommended	50 μm 2.0 mils		
<u>}</u> ↑	Flash off time @ 25C	5 to 10 mins between coats. 15 to 20 mins for 314 Slow 2K Polyurethane Base.		
	Drying	Air Dry @	∄ 25°C	Tack free: 4 hours. Recoatable with itself after at any time.

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

Before Use			
	Stir all products thoroughly each time before use. Stir the mixture well after the weigh out of components.		
	Before application a colour comparison is <b>STRONGLY</b> recommended.		
<b>○</b> F/ °C	Surface temperature must always be a minimum of 3°C above dew point.		

Dry Film Properties (after 7 days drying, when compared to similar technology products)			
Gloss 60/20	50%		
Water resistance	Excellent.		
Petrol resistance	Excellent.		
Durability	Excellent.		

# **Equipment Cleaning**

Use Haymes Paint Industrial Coating Solutions 2K Thinner or Multi Thinner

#### Storage

Read the Safety Data Sheet (SDS) for this product for specific directions on storage (section 7 of the SDS) and transport (section 10 of the SDS). To obtain a copy of the SDS, go to the Haymes Paint website,

https://www.haymespaint.com.au/products/technical/product-data-sheets-and-safety-data-sheets/, or contact Haymes Service Express on 1800 033 431. Containers must be secured and stored upright during transit. Protect from extremes of temperature. Store in a cool, dry, well-ventilated place and out of direct sunlight. Check regularly for leaks. Ensure the container label remains legible for future identification and usage.

# Coverage

Approximately 8.0 m<sup>2</sup>/L @ recommended DFT.

Shelf Life: 36 months in an unopened container at room temperature away from sunlight.

### Safety & First Aid

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public.

Read the Safety Data Sheet (SDS) for this product, prior to using this product. The SDS contains important information on how to use this product safely including hazards and precautions, personal protective equipment, storage and first aid in the event of an emergency. To obtain a copy of the SDS, go to the Haymes Paint website,

https://www.haymespaint.com.au/products/technical/product-data-sheets-and-safety-data-sheets/, or contact Haymes Service Express on 1800 033 431.

If the product is swallowed, phone the Poisons Information Centre on 13 11 26 or contact a Doctor. Keep out of reach of children. Avoid contact with skin and eyes. Wear suitable, protective clothing, eye protection and impervious gloves when mixing and using.

#### **Protect our environment**

Do NOT pour any leftover product down the drain. Retain in a marked, sealed container for future use or disposal via chemical waste collection programs such as Paintback ®. Visit www.paintback.com.au for details of your nearest depot. Dried empty containers can be recycled and should be disposed of via recycling facilities.

### Manufacturer's comment

This product has been designed as part of an integrated application system. Use with any other manufacturer's product(s) or failing to follow application instructions, could result in detrimental effects on product performance, for which Henry Haymes Pty. Ltd. cannot be held responsible. Important safety information is available on the Safety Data Sheet available from Haymes Paint website www.haymespaint.com.au. Further information about other Haymes products recommended to be used in conjunction with this product are available from the website in the form of Product Data Sheets in relation to those products. We are continually updating materials and methods, so please ensure you have the latest information on the Haymes Paint website.

#### Disclaimer

The information provided in this Product Data Sheet is correct at the time of preparation, but is subject to change. It is your responsibility to check the Haymes Paint website at www.haymespaint.com.au to ensure that you have the most current Product Data Sheet. Product application and performance is affected by environmental conditions at the time of application and drying. Paint applied in conditions outside of what is recommended may dry more slowly or be less durable or produce a less uniform appearance.

Henry Haymes Pty Ltd A.B.N. 14 004 201 638 Waringa Drive Wendouree Industrial Estate Ballarat Vic 3350 Free call 1800 033 431 Free fax 1800 801 892 www.haymespaint.com.au

Version	Version number	Date
Current	3.0	12/05/2023
Supersedes	2.0	28/01/2022