

Quick Reference Roof Coating Guide

Product	Thinning	Compatible with	Recoat @ 25°C	External	Uses	Additional	Application Rate per coat	Tip Size
Primers:								
NuPrime	No Dilution	All roof top coats	2 hours	Yes	Powdery oxidised roof tiles and paint	Saturation coating milky dries clear	1 coat @4sq.m/litre	519-521
SupaPrime	No Dilution	All roof top coats	2 hours	Yes	Powdery oxidised roof tiles and paint	Saturation coating milky dries clear	1 coat @4sq.m/litre	519-521
Master Sealer	No Dilution	All roof top coats	2 hours	Yes	Stable cement roof tiles and paint	Saturation coating milky dries clear	1 coat @4sq.m/litre	519-521
Nubond	No Dilution	All roof top coats	4 hours	Yes	Newer, shiny roof tiles	Milky dries clear	1 coat @4sq.m/litre	519-521
FlexiPrime	No Dilution	All roof top coats	24 hours	Yes	Unstable previously painted surfaces	Can be tinted to most colours	1 coat @4sq.m/litre	523-525
GP Primer	No Dilution	All roof top coats	4 hours	Yes	Very rough cement roof tiles	Light Grey colour	1 coat @4sq.m/litre	523-525
Metal Primer	No Dilution	All roof top coats	4 hours	Yes	Metal sheet roofing	Light Grey colour	1 coat @ 6sq.m/litre	523-525
Elite Terracotta Primer	No Dilution	All roof top coats	2 hours	Yes	Raw uncoated, glazed & vitrified terracotta tiles	Milky White	1 coat @12sq.m/litre	519-521
Asbestos Sealer	No Dilution	All roof top coats	2 hours	Yes	Asbestos sheeting	Opaque White	1 coat @4sq.m/litre	519-521
Top Coats:								
NuFlex	No Dilution	All roof primers & Sealers	2 hours	Yes	Trade Quality	10 year warranty	2 coats @4sq.m/litre	519-523
TileFlex	No Dilution		2 hours	Yes	Premium Quality	12 year warranty	2 coats @4sq.m/litre	519-523
NXT Cool Zone (Gloss & Low Sheen)	No Dilution		2 hours	Yes	Ultra Premium Heat Reflective	15 year warranty	2 coats @4sq.m/litre	519-523
FlexiShield (Low Sheen & Matt)	No Dilution		4 hours	Yes	Mainly for Metal Surfaces	10 year warranty	2 coats @5sq.m/litre	519-523
Other products:								
Aqua Stop Silicon Sealer	No Dilution	Silicon in water	1 hour	Yes	Most porous surfaces	Do Not allow to pool on surface	2 coats @3sq.m/litre	515-519
Terraglaze	No Dilution	Silicon modified	4 hours	Yes	Porous, unglazed terracotta & concrete tiles	Clear	2 coats @5sq.m/litre	519-521

* This is a quick reference guide only

** Primers and Sealers must be top coated

*** For complete information on all products refer to Nutech Product Data Sheets, Application Guidelines and Material Safety Data Sheets