

Nutech Quick Reference Floor Coating Guide



Product	1st Coat	Compatible with	Pot Life	Recoat @ 20°C	Internal	External	Uses	Application Rate per coat	Additional
PaveCoat	20% NT Thinners 50% smooth surface	Single pack Solvent acrylic	N/A	1-2 hours	Yes	Yes	Driveways, Floors Garage, Factory	2 coats @ 4-5 sq.m/lt	Easy recoat economical
PR 200 PR210	20% PR Thinners 50% smooth surface	Single pack Solvent acrylic	N/A	1-2 hours	Yes	Yes	Workshop floors Petrol stations	2 coats @ 4-5 sq.m/lt	Petrol Resistant
EPiC Epoxy 500 (all colours)	20% Epoxy Thinners	Epoxy Coatings	5 hours 2 Component	4-5 hours within 48 hours	Yes	No	Factory floors Swimming pools	2 coats @ 6-8 sq.m/lt	Overcoat with Epoxy
EPiC Polycryl (clear & colours)	20% Polycryl Thinners	Polycryl ok over PaveCoat	8 hours 2 Component	2-4 hours within 12 hours	Yes	Yes	Factory floors Driveways	2 coats @ 8 sq.m/lt	Overcoat with Polycryl
Aqua Floor (clear & colours))	20% Clean Water	Aqua Epoxy	2 hours 2 Component	8-10 hours within 24 hours	Yes	Yes	Factory floors Show rooms	2 coats @ 8 sq.m/lt	Goes on milky Low odour
Aqua Epoxy (clear only)	20% Clean Water	Aqua Floor	2 hours 2 Component	4-5 hours within 24 hours	Yes	No	Factory floors House slabs	2 coats @ 8 sq.m/lt	Goes on milky Low odour
EPiC Industrial Enamel (all colours)	20% Min. Turpentine	Industrial Enamel	N/A	2-4 hours	Yes	No	Workshop floors Factory floors	2 coats @ 8-15 sq.m/lt	Only overcoat with Enamel Oil/Grease tolerant
Silicon Sealer	No dilution	All top coats	N/A	30 minutes	Yes	Yes	Terra cotta tile, Brick & Cement	1 or 2 coats @ 0.5 to 3 sq.m/lt	Do not allow to pool on surface
Limestone Sealer	No dilution	Do not top coat	N/A	1 coat only	Yes	Yes	Natural & reconstituted Limestone/Sandstone	0.5 to 3 sq.m/lt depend on pourosity	Only 1 coat do not apply 2nd coat
Aqua Stop Silicon Sealer	No dilution	Aqua Stop Silicon Sealer	N/A	2 coats	Yes	Yes	Natural stone Bluestone	1 or 2 coats @ 0.5 to 3 sq.m/lt	Test Bluestone prior to coating
SO 2000	No Dilution	Single pack Solvent acrylic	N/A	1 - 2 hours	Yes	Yes	Clear Sealer for Spray On Decorative Concrete	2 coats @ 4-6 sq.m/lt	Less Polymer Fast dry, Non salt Efflorescence
Pavecoat H2o	20% Clean Water	Etched Bare Concrete	N/A	1 hours	Yes	Yes	Driveways, Floors Garage, Factory	2 coats @ 6-8 sq.m/lt	Easy recoat Economical Low odour

* This is a quick reference guide only

Nutech Quick Reference Floor Coating Guide0117

** For complete information on all product refer to Nutech Product Data Sheets, Application Guidelines and Material Safety Data Sheets

Non porous concrete should be washed with hydrochloric acid or Nu-Ecosafe Concrete Etch 1 part to 10 parts water for smooth and 1 part to 15 parts water for rough concrete