

Technical Data Sheet

Asbestos Sealer

Product	Application of Asbestos Sealer prevents dusting and deterioration of Asbestos sheeting,
Description	protecting adjacent environments from the risk of Asbestos related health problems.
	Asbestos Sealer is a cross linking alkaline curing acrylic emulsion designed as a
	saturation/penetration coating suitable for both porous and non-porous asbestos,
	masonry and cement sheet.
	Due to its alkaline curing functionality, Asbestos Sealer ensures greater bonding is
	achieved compared to that of standard acrylic and co-polymer emulsion sealers.
	Asbestos Sealer also provides improved adhesion and surface binding properties for a
	range of Nutech top coating systems including; NuFlex, TileFlex or NXT Cool Zone .
	 Excellent adhesion to weathered and porous Asbestos surfaces
	Ambient temperature cross-linking
Asbestos Sealer	• Easy application by brush, roller or airless spray
Features:	Excellent chemical resistance
	Trafficable surface
	Weatherproofing performance
	High resistance to mould and fungus
	 Economical prime coat
Safety Precautions:	Observe all Occupation Health and Safety (OH&S) precautions.
Sarcty recoulions.	Refer to the relevant Safety Data Sheets (SDS) for product safety related information.
	For further information and support: Nutech Paint 03 9770 3000
	www.nutechpaint.com.au
	www.nutechpaint.com.au
Provisions:	DO NOT mechanically clean or high-pressure clean Asbestos.
Provisions:	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES
	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL.
Chemical Type:	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer
	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL.
Chemical Type:	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer
Chemical Type:	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre
Chemical Type:	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0
Chemical Type:	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water
Chemical Type:	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C.
Chemical Type: Product Attributes	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C. Minimum Film Thickness (dry): 20 - 25 microns
Chemical Type: Product Attributes Typical	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C. Minimum Film Thickness (dry): 20 - 25 microns Typical projects include:
Chemical Type: Product Attributes Typical	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C. Minimum Film Thickness (dry): 20 - 25 microns Typical projects include: Domestic & Multi Density Residential, Industrial and Commercial uses for priming and
Chemical Type: Product Attributes Typical Applications	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C. Minimum Film Thickness (dry): 20 - 25 microns Typical projects include: Domestic & Multi Density Residential, Industrial and Commercial uses for priming and binding Asbestos and cement sheet.
Chemical Type: Product Attributes Typical Applications Appearance	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C. Minimum Film Thickness (dry): 20 - 25 microns Typical projects include: Domestic & Multi Density Residential, Industrial and Commercial uses for priming and binding Asbestos and cement sheet. Opaque white or off-white viscous liquid
Chemical Type: Product Attributes Typical Applications Appearance Coverage / Spread	DO NOT mechanically clean or high-pressure clean Asbestos. Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIES REGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL. Styrene-acrylate copolymer Total VOC (Material): 59 g/litre pH: 8.5 – 9.0 Solubility: Soluble in Water Minimum Film Forming Temperature: 10°C. Minimum Film Thickness (dry): 20 - 25 microns Typical projects include: Domestic & Multi Density Residential, Industrial and Commercial uses for priming and binding Asbestos and cement sheet. Opaque white or off-white viscous liquid 4m²/L per coat
Chemical Type: Product Attributes Typical Applications Appearance Coverage / Spread	DO NOT mechanically clean or high-pressure clean Asbestos.Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIESREGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL.Styrene-acrylate copolymerTotal VOC (Material): 59 g/litrepH: 8.5 – 9.0Solubility: Soluble in WaterMinimum Film Forming Temperature: 10°C.Minimum Film Thickness (dry): 20 - 25 micronsTypical projects include:Domestic & Multi Density Residential, Industrial and Commercial uses for priming andbinding Asbestos and cement sheet.Opaque white or off-white viscous liquid 4m²/L per coatNote: Coverage will depend on the porosity and roughness of the surface.
Chemical Type: Product Attributes Typical Applications Appearance Coverage / Spread Rate	DO NOT mechanically clean or high-pressure clean Asbestos.Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIESREGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL.Styrene-acrylate copolymerTotal VOC (Material): 59 g/litrepH: 8.5 – 9.0Solubility: Soluble in WaterMinimum Film Forming Temperature: 10°C.Minimum Film Forming Temperature: 10°C.Minimum Film Thickness (dry): 20 - 25 micronsTypical projects include:Domestic & Multi Density Residential, Industrial and Commercial uses for priming andbinding Asbestos and cement sheet.Opaque white or off-white viscous liquid 4m²/L per coatNote: Coverage will depend on the porosity and roughness of the surface.To maximise performance do not over spread.
Chemical Type: Product Attributes Typical Applications Appearance Coverage / Spread Rate Packaging	DO NOT mechanically clean or high-pressure clean Asbestos.Prior to carrying out any treatment of asbestos, CHECK WITH LOCAL AUTHORITIESREGARDING SPECIFIC GUIDELINES IN THE TREATMENT OF THIS MATERIAL.Styrene-acrylate copolymerTotal VOC (Material): 59 g/litrepH: 8.5 – 9.0Solubility: Soluble in WaterMinimum Film Forming Temperature: 10°C.Minimum Film Thickness (dry): 20 - 25 micronsTypical projects include:Domestic & Multi Density Residential, Industrial and Commercial uses for priming andbinding Asbestos and cement sheet.Opaque white or off-white viscous liquid 4m²/L per coatNote: Coverage will depend on the porosity and roughness of the surface.To maximise performance do not over spread. 2L, 4L, 10L, 20L and 1000L



Substrate

Recommendations: Asbestos and cement sheet.


NOTE	 Do not apply in temperatures under 12 Degrees Celsius or late in the day and allow for adequate drying time. In cold weather do not overcoat until the first coat is fully dried. Avoid painting in high temperatures to avoid damage and ensure surface adhesion.
Mixing/ Thinning	Prior to Commencement: Stir thoroughly prior to use. Maximum dilution: 10%.
Test Patch	Conduct a small test patch to ensure adequate product performance and adhesion.
Substrate note:	Clean the substrate as best as possible without disturbing the surface.
Application	Brush Roller Airless Spray
Procedure:	High pressure cleaning in the treatment of asbestos surfaces <u>IS PROHIBITED</u> .
	Any equipment to be used in the treatment and disposal of Asbestos must be done so in accordance with controlled regulatory guidelines and conducted by TRAINED PROFESSIONALS.
	 Pre-treatment: with Nutech Hypo or Nu-EcoSafe MossRid is recommended. <u>Very low-pressure</u> water washing only, is recommended to avoid asbestos dust becoming generated.
	 Application: Application by airless spray, brush or roller <u>to saturation point</u> is required to maximize surface binding properties.
	Application in cooler weather is recommended to ensure maximum penetration of Asbestos Sealer.
Drying Time	Ambient conditions @ 25°C and 50% relative humidity. Touch Dry 30 Minutes.
Recoat	Recoat 2 hours at cooler temperatures or higher humidity drying times will be extended. Recoat 3 hours.
Clean Up	Protecting Our Environment is important to Nutech Paints: Clean up hands and equipment with fresh warm water or dispose of equipment. Do not pour left over paint down drains or in rubbish bins. Unwanted paint should be kept in a sealed container and then disposed of via special waste collection services. Empty paint containers should be left open in a well ventilated area to dry out. Dispose of empty paint containers in accordance with local authority guidelines. Always check with your local council first.

First Aid



SEEK IMMEDIATE MEDICAL ATTENTION. Refer to the appropriate *Nutech Material Safety Data Sheet* (MSDS) for further information. For medical emergencies only, call: 000

- In case of eye contact, flush thoroughly with water for at least 15 minutes.
- In case of skin contact, wash affected areas with soap and water. If irritation persists.
- Remove and wash contaminated clothing.
- If inhalation causes physical discomfort, remove to fresh air.
- If discomfort persists, or any breathing difficulty occurs or if swallowed seek medical advice.





Nutech Paint PTY LTD ©03 9770 3000 @sales@nutech.com.au www.nutechpaint.com.au