

Technical Data Sheet

AntiSlip Cast On

Product Description

AntiSlip Cast On is a crystalline thermoplastic polymer developed as an anti slip cast on additive exhibiting high tensile and flexural strength. AntiSlip Cast On significantly increases the friction coefficient of a coated surface, reducing slip potential under both wet and dry conditions and is been designed to be hand broadcast onto the surface to the range of Nutech Paint 2 pack floor coating systems such as; EPiC Epoxy 500, EPiC PolyCryl, EPiC AquaFloor, EPiC AquaEpoxy.

AntiSlip Cast On Features:

AntiSlip Cast On when applied in the correct methods, will achieve a Pendulum Classification of P4 (Fine Grade) or P5 (Coarse Grade) and meets AS4586 & AS4663. Please refer to the Nutech Paint AntiSlip Skid Test Fact Sheet for further details.

- Available in 2 granular sizes: Fine & Coarse
- Substantially improves safety of sealed surfaces in wet and dry conditions
- Chemically inert and non-hazardous
- Resistant to UV light, mild acids and alkali, stains, salts and dirt
- Flexible and scuff resistant
- Non-yellowing and resistant to moisture
- Resists fungi and bacteria attack

Safety Precautions:	Observe all Occupation Health and Safety (OH&S) precautions. Refer to the relevant Safety Data Sheets (SDS) for product safety related information. For further information and support: Nutech Paint 03 9770 3000 www.nutechpaint.com.au
Provisions:	AntiSlip Cast On IS NOT suitable for use in single pack coatings such as Pavecoat. AntiSlip Cast On can achieve up to an R12 or P5 slip rating. AntiSlip IS NOT to be used in AguaStop or Silicon Sealer

	Antishp is NOT to be used in Aquastop of shicon sealer
	Not Suitable for Clear Coatings
Chemical Type:	Crystalline Thermoplastic Polymer
Product Attributes	Solubility in Water: Nil

Solubility in Solvent: Nil Softening point: 166-168°C.

Typical	 External ramps steeper than 1:14
Applications	 Loading docks,
	Commercial kitchens
	 Swimming pool ramps and stairs.
Appearance	Off White to Light Brown Crystals
Coverage / Spread	1kg / 2-5 square metres cast onto the surface of the first wet coat.
Rate	
Packaging	7kg (4lt Pail) 25kg – Pail
Storage	Cool, dry location. Avoid contact with extreme heat.
Shelf life	Unlimited storage when not exposed to moisture or extreme heat.



	Tota periect illiisti:
Substrate Recommendations	All painted surfaces that require a non-slip textured finish.
NOTE	MUST BE TOP COATED to lock AntiSlip Cast On into coating.
Mixing/ Thinning	N/A. To be Broadcast onto Nutech 2 Pack products
Test Patch	Nutech Paint recommends that applicators test any AntiSlip system first as varying surface profiles, slopes and access conditions vary significantly with individual conditions. These variants impact heavily on pedestrian and vehicle safety.
Substrate note:	Refer to specific Nutech Paint product TDS for specific application guidelines
Application	Hand broadcast onto wet 2 pack surface.
Procedure:	Preparation: Identify all areas to have non slip material applied. Prepare surface to be coated with the required Nutech 2 pack system, in accordance with the relevant TDS observing all preparation pretreatments and dry times.

Pre-mix the required Nutech 2 pack system in accordance with the relevant TDS

Application:

- Apply the first coat of the required Nutech 2 pack system in accordance with the relevant TDS.
- While the first coat is still wet, broadcast the AntiSlip Cast On in 1m square sections at a time, ensuring consistent and even distribution. Allow coating to cure.
- Once the first coat is dry prior top coating, lose or excess **AntiSlip Cast On** can be removed either by brush and/or vacuum.
- Apply the Nutech 2 pack system top coat in accordance with the relevant TDS to "lock in" the **AntiSlip Cast On** and allow to fully cure.

Note: When using the coarse grade **AntiSlip Cast On**, an increased application rate of the top coat will be required due to an increase of the surface area.



Classification

AS 4586, slip resistance classification of new pedestrian surface materials. AS 4663, slip resistance measurement of existing pedestrian surfaces

AntiSlip Addition	Nutech Product	Rating
AntiSlip Cast On – Fine	EPiC Epoxy 500, Epic PolyCryl,	
Applied at 2-5m2 / 1kg cast	AquaFloor and AquaEpoxy.	
onto wet surface. Must be top		Wet P4
coated to encapsulate Anti-		
Slip.		
AntiSlip Cast On - Coarse	EPiC Epoxy 500, Epic PolyCryl,	
Applied at 2-5m2 / 1kg cast	AquaFloor and AquaEpoxy.	
onto wet surface. Must be top		Wet P5
coated to encapsulate Anti-		
Slip.		

Drying Time	Refer to specific Nutech 2 pack system TDS for product drying times
Recoat	AntiSlip Cast On is to be added to the wet first coat only.
	Refer to specific Nutech 2 pack system TDS for recoat times
Clean Up	Refer to specific Nutech 2 pack system TDS for clean up recommendations

First Aid

SEEK IMMEDIATE MEDICAL ATTENTION. Refer to the appropriate *Nutech Material Safety Data Sheet* (MSDS) for further information.

For medical emergencies only, call: 000

- In case of eye contact, flush thoroughly with water for at least 15 minutes.
- In case of skin contact, wash affected areas with soap and water. If irritation persists.
- Remove and wash contaminated clothing.
- If inhalation causes physical discomfort, remove to fresh air.
- If discomfort persists, or any breathing difficulty occurs or if swallowed seek medical advice.



Warranty

Nutech warrants its products to be free from defects in material and workmanship. Nutech's sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at Nutech's option, to either replacement of products not conforming to this Warranty or credit to Buyer's account in the invoiced amount of the nonconforming products.

Any claim under this Warranty must be made by Buyer to Nutech in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify Nutech of such non-conformance as required herein shall bar Buyer from recovery under this Warranty.

Nutech makes no other warranties concerning the product. No other warranties, whether express, implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall Nutech be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by Nutech, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

Limitation of Liability

Nutech's liability on any claim of any kind, including claims based upon Nutech's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which gives rise to the claim. In no event shall Nutech be liable for consequential or incidental damages.

Disclaimer

The information given on this data sheet is based on many years' experience and is correct to the best of our knowledge. However, since the use of our product, surface conditions, weather and a number of other factors are completely beyond our control, we can only be responsible for the quality of our product at the time of dispatch. For more information please contact our Company. As this information is of a general nature, we cannot assume any responsibility in individual cases.'

The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.



Nutech Paint PTY LTD

©03 9770 3000

■sales@nutech.com.au

www.nutechpaint.com.au